

REFERENCE LIST

- Acetta, A. and Vergnand, J.M. (1981) Upgrading of scrap rubber powder by vulcanization without new rubber, *Rubb. Chem. Technol.*, 54, pp.302-310.
- Adam, G., Sebenik A., Osredkar, U., Veksil, Z. and Ranogajec, F. (1991) The possibility of using grafted waste rubber, *Rubb. Chem. Technol.*, 64, p.133.
- Adhikari, B., De D. and Maiti, S. (2000) Reclamation and recycling of waste rubber, *Progress in Polymer Science*, 25, p.909.
- Adhikari, B., Maiti, D. and De S. (2000) Reclamation and recycling of waste rubber, *Progress in Polymer Science*, 25, pp. 909-948.
- Alger, M.S.M. and Dyson, R.W (1990). Thermoplastic Composites (Chap.1). In R.W. Dyson (Ed.), *Engineering Polymers* . USA: Chapman & Hall, New York : Blackie & Son Ltd.
- Amme, R.C., Meredith, G., Gould, N. and Laramie, N. (2003). *Resources Recycling*, 22, p.32.
- Anderson E. Jr. (1985), U.S. Pat. 4,544,675.
-  University of Moratuwa, Sri Lanka.
Avgeropoulos, N., Weissert, F.C., Biddison, P.H. and Bohm, G.G.A. (1976), Heterogeneous blends of polymers. Rheology and morphology, *Rubb. Chem. Technol.*, 49, p.93. www.lib.mrt.ac.lk
- Bandyopadhyay, S., Dasgupta, S., Agrawal, S.L., Mandot, S.K., Mandal, N., Mukhopadhyay, R., Deuri, A.S. and Ameta Suresh C. (2006) Use of recycled tyre material in NR/BR blend based tyre tread compound: Part I (with ground crumb rubber), *Progr. Rubber Plast. Recycl. Technol.*, 22, No.1, p.45.
- Bandyopadhyay, S., Dasgupta, S., Mandal, N., Agrawal, S.L., Mandot, S.K., Mukhopadhyay, R., Deuri, A.S. and Ameta Suresh C. (2005) Use of recycled tyre material in natural rubber based tyre tread cap compound: Part 1 (with ground crumb rubber), *Progr. Rubber, Plast. Technol.*, 21 (4), pp.299-317.
- Batchelor, J.D., Carpenter, E.E., Holder, G.N., Eagle, C.T., Fielder, J. and Cummings, J. (1998) Recreation of Wohler's synthesis of urea: An undergraduate organic laboratory exercise, *The Chemical Educator*, Vol.3, No. 6, Springer-Verlag, New York, Inc.
- Billmeyer, Jr. Fred W. (1971). *Textbook of Polymer Science* (2nd ed.). New York: John Wiley & Sons Inc.

Blow, C.M. (1971). *Rubber Technology and Manufacture*. London: Butterworth & Co.

Bohn, L. (1968), Incompatibility and phase formation in solid polymer mixtures and graft and block copolymers, *Rub. Chem. Technol.*, 41, p.495.

Bokobza, L. and Rapoport, O. (2002). Reinforcement of natural rubber. *J. Appl. Polym. Sci.*, 85, pp. 2301-2316.

Boonstra, B.B. and Dannenberg, E.M. (1959). Swelling behaviour of rubbers compounded with reinforcing pigments. *Rubb. Chem. Technol.*, 32, p.825.

Braton N.R. and Koutsky J.A. (1974). *Chem. Eng. News*, 52(6), p.21.

Bristow, G.M. (1978), *NR Technol.*, 9(1), p.1.

Burgoyne, M., Leaker, G. and Krekic, Z. (1976), The effect of reusing ground flash and scrap rubber in parent compound, *Rubb. Chem. Technol.*, 49, p.375.

Callan, J.E., Topcik, B. and Ford, F.P. (1965). *Rubber World*, 151 (6), p.60.

Carlsson, D.J. and Wiles, D.H. (1974). *Rubb. Chem. Technol.*, 47, pp. 976-990.

Chapman, A.V. and Porter, M. (1988). Sulphur vulcanization chemistry. In A.D. Roberts (Ed.) *Natural Rubber Science and Technology*. p.511-620. New York: Oxford University Press.



Chiang, Huang (1999) Compounding and compatibilization of high-performance polymer alloys and blends. In Shonaike, G.O. and Simon, G. Eds., *Polymer Blends and Alloys*, p.23-52, Marcel Dekker, New York.

Cho, K. and Lee, D. (2001). *Polymer*, 41, p.133.

Cialone, A.M., Banda, M. and Smith Jr., D.W. (2008). “ Novel method for cryogenic grinding of vulcanized rubber for utilization in tyre compounds”. Paper presented at a meeting of the Rubber Division, ACS, 16-18 October, Cleveland, OH, Paper # 97.

Coleman, M.M., Moskala, E.J., Painter, P.C., Walsh, D.J. and Rostami, S. (1983). A Fourier transform infra-red study of the phase behaviour of polymer blends. Ethylene-vinyl acetate copolymer blends with poly(vinyl chloride) and chlorinated polyethylene. *Polymer*, 24, pp.1410-1414.

Coran, A.Y. (1978). Chapter 7. In Eirich, F.R. (Ed.), *Science & Technology of Rubber*. New York: Academic Press.

Corish, P.J.(1967), Fundamental studies of rubber blends, *Rub. Chem. Technol.*, 40, p.324.

Cruz, C.A., Barlow, J.W. and Paul, D.R. (1979), The basis for miscibility in polyester-polycarbonate blends, *Macromolecules*, 12, No. 4, July-August, p.726.

Dean, John A. (1995). *The Analytical Chemistry Handbook*. pp. 15.1–15.5. New York: McGraw Hill.

Deanin and Manion (1999) Compatibilisation of polymer blends. In G.O. Shonaike and G. Simson (Eds.), *Polymer blends and alloys*, p.1-23, New York: Marcel Decker.

De D., Adhikari B., and Maiti S. (1997) Reclaiming of rubber by a renewable resource material, Part 1, *J. Polym. Mater.*, 14, p.333.

De Debapriya, Das Amit, De Debasish, Dey Brojendranath, Debnath Subhas Chandra, Roy Bidhan Chandra (2006). Reclaiming of ground rubber tyre (GRT) by a novel reclaiming agent. *European Polymer Journal*, 42, pp.917-927.

De Debapriya and De Debasish (2011). Processing and material characteristics of a reclaimed ground rubber tyre reinforced styrene butadiene rubber. *Mat. Sci. Appl.*, 2, pp.486-496.

De Debapriya, De Debasish and Singharoy G.M. (2007). Reclaiming of ground rubber tyre by a novel reclaiming agent. I. Virgin natural rubber / reclaimed GRT vulcanizates. *Polym. Eng. Sci.*, 47, Issue 7, pp.100-1091.

De D., Maiti S., and Adhikari B. (1999) Reclaiming of rubber by a renewable resource material (RRM), Part 11, Comparative evaluation of reclaiming process of NR vulcanisate by RRM and diallyl disulfide, *J. Appl. Polym. Sci.*, 73(14), p. 2951.

De Debapriya, Maiti Sukumar and Adhikari Basudam (2000). Reclaiming of rubber by a renewable resource material (RRM) III . Evaluation of properties of NR reclaim. *J. Appl. Polym. Sci.*, 75, pp.1493-1502.

De-Link Bulletin 1 (1995), De-Link recycling system, all you want to know. Kuala Lumpur: STI-K Polymers Sdn. Bhd., pp.1-15.

De, S.K. (2001). Re-use of ground rubber waste. *Progr. Rubber Plast. Technol.*, 17, p.113.

Dierkes, W. (1996) Solutions to the rubber waste problem incorporating the use of recycled rubber. *Rubber World*, 25, May.

Dierkes W.(2005). Chap.3 Untreated and treated rubber powder in Rubber Recycling. In Sadhan, K, De., Avraam, I. Isayev and Klementina Khait (Eds.), *Rubber Recycling* p.139. CRC Press, Taylor & Francis Group, p.139.

Dierkes, W.K. (2003), Recent Research Developments in Macromolecules, 7, pp. 265-292.

Dietrich, K.M. and Burns, B.J. (2000), Paper presented at a meeting of the Rubber Division, ACS, 21-24 September, Orlando.

Dluzneski, P. (2001), Peroxide vulcanization of elastomers, *Rub. Chem. Technol.*, 74, p.451.

Donovan, P. (1997, November), Solid Waste Technologies, p.26.

Duhaime, J.R.M. and Baker, W.M., Plastics Rubber Composites Processing Application, 15 (1991) p.87.

Dunn, J.R. (1993), Paper presented at a meeting of the Rubber Division, 26-29 October, Orlando.

Evans, L. and Partridge, E.G. (1963), ACS/CIC, Div. Rubber Chem., 83rd Meeting, *Rubber Age*, 94(2).

Farahani, T.D., Bakhshandeh, G.R. and Abtahi, M. (2006), Mechanical and viscoelastic properties of natural rubber/reclaimed rubber blends, *Polymer Bulletin*, 56, pp. 495-505.  University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations www.lib.mrt.ac.lk

Fesus, E. (1994), Paper presented at a meeting of the Rubber Division (Paper #22), ACS, 19-22 April, Chicago.

Finar, I.L. (1973) Organic Chemistry, The Fundamantal Principles, 6th Edit., Pub. Longman Group Ltd., Essex, UK

Fix S.R. (1980). *Elastomerics*, 112(6), p.38.

Flory, P.J. and Rehner Jr. J. (1943). *J. Chem. Phys.*, 11, p.521.

Fried, J.R. (1995). Polymer Science and Technology, New Jersey: Prentice-Hall.

Fujimoto, K., Nishi, T. and Okamoto, T., (1981). *Nippon Gomu Kyokaishi*, 54(5), p.310.

Fukahori, Y. and Yamazaki, H. (1995). Mechanism of rubber abrasion part 3: how is friction linked to fracture in rubber abrasion. *Wear*, 188, pp.19-26.

Furhmann, I. and Karger-Kocsis, J. (1999), *Kautschuk Gummi Kunststoffe*, 52, p.836.

Gent, A.N. (1992). Ed., *Engineering with Rubber; How to Design Rubber Components* (p.21), Hanser.

Gibala, D. and Hamed, G.R. (1994). Cure and mechanical behaviour of rubber compounds containing ground vulcanisates Part I – Cure behaviour. *Rubb. Chem. Technol.*, 67, pp.636-648.

Gibala,D. and Laohapisitpanich, K.(1995). Cure and mechanical behaviour of the compounds containing ground vulcanisates. Part II – Mooney viscosity. Presented at the 148th ACS Rubber Division Meeting, Cleveland, OH, USA, October.

Gibala, D., Thomas, D. and Hamed, G.R., (1999). Cure and mechanical behaviour of rubber compounds containing ground vulcanisates: Part III Tensile and tear strength. *Rubb. Chem. Technol.*, 72, p.357.

Goetz, M.R. (1994) “Review of studies conducted to evaluate environmental concerns of crumb rubber modified asphalt”, Research for Asphalt Institute, USA, p.65.

Grosch, K.A. (1991) In Bhowmick, A.K. and De, S.K. (Eds.), *Fractography of Rubbery Materials*, Elsevier Science, Pub.



[University of Moratuwa, Sri Lanka](#)

Hadi, A. M. and Botka, D.E. (2007). Characterizing the effect of ultra fine scrap tire rubber on tire compound properties. Paper presented at a meeting of the Rubber Division, ACS, 16-18 October, Cleveland, OH, Paper # 97.

Hall, J.M. (1969) Recycling, production and use of recycled rubbers (Chap. 17). In Ball, J.M. (Ed.), *Introduction to Rubber Technology*, 7th edition. New York: Van Nostrand Reinhold.

Hamed, G.R. and Gibala, D. (1994). Cure and mechanical behaviour of rubber compounds containing ground vulcanizates. Part I – Cure behaviour. *Rubb. Chem. Technol.*, 67, p.636.

Hamed, G.R., Gibala, D. and Thomas, D. (1999) Cure and mechanical behaviour of rubber compounds containing ground vulcanizates: Part III. Tensile and tear strength, *Rubb. Chem. Technol.*, 72, p.357.

Han, M.H. (1998). Paper presented at the 7th International Seminar on Elastomers, 16 – 17 December, Bangkok.

Han, S.C. and Han, M.H. (2002). Fracture behaviour of NR and SBR vulcanizates filled with ground rubber having uniform particle size. *J. Appl. Poly. Sci.*, 85, p.2491.

Hershaft A.A. (1972), Solid waste, *Environ. Sci. Technol.*, 6, No. 5, May, pp.412-421.

Hess, W.M., Scott, C.E. and Callan, J.E. (1967) Carbon black distribution in elastomer blends, *Rubb. Chem. Technol.*, 40, p.371.

Hess, W.M. and Chirico, V.E. (1977), Elastomer blend properties – Influence of carbon black type and location, *Rubber Chem. Technol.*, 50, p.301.

Hildebrand, J.H. and Scott, R.L. (1964). *The solubility of non-electrolytes* (3rd ed.).New York: Dover.

Hildebrand H. (Continental Gumi-Werke, A.G.) (1967) Regeneration of synthetic rubber vulcanisates, German Pat. 1,244,390.

Horikx, M.M. (1956). *J. Polm. Sci.*, 19, pp.445-54.

Ishiaku, U.S., Chong, C.S. and Ismail, H.(1999). Determination of optimum De-Link R concentration in a recycled rubber compound. *Polymer Testing*, 18, pp.621-633.

Ismail, H., Freakley, P.K., Sutherland, I. and Sheng, E. (1995). Effects of multifunctional additive on mechanical properties of silica filled natural rubber compound, *Eur. Polym. J.*, 31, Issue 11, pp. 1109-1117.



University of Moratuwa Sri Lanka
Electronic Theses & Dissertations

Jacob, Ceni and De, SKW(2005) Powdered Rubber Waste in Rubber Compounds (Chap.6). In Sadhan K. De, Avraam I. Isayev and Klementina Khait (Eds.), *Rubber Recycling*. USA: CRC Press, Taylor & Francis Group.

Jana, G.K. and Das, C.K. (2005) Devulcanisation of natural rubber vulcanisates by mechanochemical process, *Poly. Plast. Technol. Eng.*, 44, pp. 1399-1412.

Kaisersberger, E., Knappe, S. and Mohler, H. (1993), TA for Polymer Engineering DSC-TG-DMA, NETZSCH Annual for Science and Industry, Vol.2, NETZSCH-Geratebau GmbH, D-95100 Selb Pub., p.11.

Kawabata N., Okuyama B. and Yamashita S. (1981), Reclamation of vulcanized rubber by chemical degradation. XV. Degradation of vulcanized synthetic isoprene by the phenylhydrazine-iron (II) chloride system, *J. Appl. Polym. Sci.*, 26, p.1417.

Kerrutt, G., Blumel, N. and Weber, H. (1969), *Kautsch. Gummi. Kunstst.*, 22 (8), p.413.

Khanna, B.B. (1998), Chemistry and Technology of Rubber, p.56.

Kim, J.K., Fracture behaviour of crumb rubber-filled elastomers (1999), *J. Appl. Polym. Sci.*, 74, p.3137.

Kim, J.K. and Burford, R.P.(1998) Study on powder utilization of waste tyres as a filler in rubber compounding, *Rubb. Chem. Technol.*, 71, p.1028.

Kim, J.K. and Lee, S.H. (2000). New Technology of Crumb Rubber Compounding for Recycling of Waste Tyres. *J. Appl. Polym. Sci.*, 78, pp. 1573-1577.

Kluppel, M. and Kahrke, A. (1997). Wiederverwendung von Altgummi in technischen Elastomerartikeln. *Kautschuk Gummi Kunststoffe*, 5, p.373.

Knorr K. (1994). *Kautschuk Gummi Kunststoffe*, 47, p.54.

Kohler R. and O'Neil J(1977). *Rubber World*, 216(2), p.32.

Kraus, G. (1965). *Reinforcement of Elastomers*. New York: Wiley Interscience.

Kraus, G. (1963). *Rubb. Chem. Technol.*, p.861.

Kumnuantip, C. and Sombatsompop, N. (2003). Dynamic mechanical properties and swelling behaviour of NR/reclaimed rubber blends. *Materials Letters*, 57, pp. 3167-3174.

 University of Moratuwa, Sri Lanka.
Kumnuantip, C. and Sombatsompop, N. (2005) Effect of reclaimed rubber content in NR / carbon black vulcanisates using microwave irradiation system. ANTEC, pp.3211-3215.

Le Beau, D.S.(1967) Science and technology of reclaimed rubber, *Rubb. Chem. Technol.*, 40, p.217.

Leblanc, J.L. (2000). Elastomer-filler interactions and the rheology of filled rubber. *J. Appl. Polym. Sci.*, 78, pp.1541-1550.

Lee, S., Azzam, F.O. and Kocher, B.S. (1996), US Patent, 5516952.

Lemieux, P. and Ryan, J.V. (1996), *Air Waste*, 43, p.1106.

Levin Yu.V., Kim S.H., Isayev A.I., Massey J., and von Meerwall E., (1996) Ultrasound devulcanisation of sulphur vulcanized SBR: Crosslink density and molecular mobility, *Rubb. Chem. Technol.*, 69, p.104.

Li, S., Lamminmaki, J. and Hanhi, K. (2005). Effect of ground rubber powder and devulcanisates on the properties of natural rubber compounds. *J. Appl. Polym. Sci.*, 97, pp. 208-217.

Lieu, H.S., Mead, J.L. and Stacer, R.G., (2000) Environmental effects of recycled rubber in light-fill applications, *Rubb. Chem. Technol.*, 73, p.551.

Liptrot, G.F. (1974). Ed., *Modern Inorganic Chemistry*, Low-priced edition, Mills & Boon Ltd., London, pp.300-301.

Mahdi, H.H. (1990). *Ph.D. Thesis*, Loughborough University of Technology, UK.

Mahlke, D. (1993), *Kautschuk Gummi Kunststoffe*, 46, p.889.

Makarov, V.M., Zakharov, N.D., Gracheva, G.N. and Vil'nits, S.A. (1975). *Kauch. Rezina*, 10, p. 21.

Manuel, H.J. (2001), *Kautschuk Gummi Kunststoffe*, 54, p.101.

Mark, H.F., Bikales, N.M., Overberger, C.G. and Menges, G. (1988) Encyclopedia of Polymer Science and Engineering, Willey Pub., 14, p.787.

Mauro, P.J., de Rubber, J. and Etienne, J.P. (1990). New rheometer and Mooney technology. *Rubber World*, January.

Mc Donel, E.T., Baranwal, K.C. and Andries, J.C. (1978).In D.R. Paul and S. Newman (Eds.), *Polymer blends*. New York: Academic Press.

McKie Douglas (1944) Wohler's synthetic urea and the rejection of vitalism: A chemical legend. *Nature*, 153, pp. 608-610.
 University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

Menadue F.B. (1945) Some technical aspects of rubber reclaiming, *Rubber Age*, 56, p.511.

Morrison, N.J. and Porter, M (1983) Temperature effect on structure and properties during vulcanization and service of sulphur cross-linked rubbers. *Plastic and Rubber Processing Applications.*, Vol.3, No. 4.

MPI (Ministry of Plantation Industries) (2011). Rubber Sector (Chapter 3). *Statistical Information on Plantation Crops – 2010*. Plantation Sector Statistical Pocket Book – 2010. Colombo: State Printing Corporation.

Myhre, M. (2005). Chap.10. Devulcanization by chemical and thermomechanical means. In Sadhan, K, De., Avraam, I. Isayev and Klementina Khait (Eds.), *Rubber Recycling*, p.146. CRC Press, Taylor & Francis Group.

Myhre, M. and Mackillop, D.A. (2000) Compounding with regenerated rubber, *RubberDivision, ACS*, October , Paper # 110.

Myhre, M. and Mackillop, D.A. (2003) Rubber recycling, *Rubb. Chem. Technol.*, 75, p.429.

Myhre, M., Unpublished data.

Myhre, M.J. and MacKillop, D.A.(1995) Modification of crumb rubber, Paper presented at a meeting of the Rubber Division, ACS, 17-20 October, Cleveland, Paper # 21.

Nasakar, A.K. and Bhowmick, A.K. and De, S.K. (2002). Melt-processable rubber: Chlorinated waste tyre rubber-filled polyvinyl chloride. *J. Appl. Polym. Sci.*, 84, p. 622.

Nasakar, A.K., De, S.K. and Bhowmick, A.K. (2002). Thermoplastic elastomeric composition based on maleic anhydride-grafted ground rubber tyre, *J. Appl. Polym. Sci.*, 84, p.370.

Nasakar, A.K., De, S.K., Bhowmick, A.K., Pramanik, P.K. and Mukhopadhyay, R., (2001), Surface chlorination of ground rubber tyre and its characterization, *Rubb.Chem.Technol.*, 74, p.645.

Nielsen, L.E. (1953), *J.Am.Chem.Soc.*, 75, p.1435.

Okamoto H., Inagaki S., Onauchi Y., and Furukawa J.(1979), *Nippon Gomu Kyokaishi*, 52(12), p.774.

Olabisi, O. (1979), "Polymer Miscibility", Academic Press, New York.
 University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations

Oliphant, K. and Baker, W. (1993). The use of cryogenically ground rubber tyres as a filler in polyolefin blends, *Polym. Eng. Sci.*, 33, p.166.

Oliveira L. and Carlos L., *Chem. Abstr.*, 106 (1987) P34401d.

O'Neill, M.J. (1964). *Anal. Chem.* 36, pp.1238–1245.

Onouchi, Y., Inagaki, S., Okamoto, H., Furukawa, J. (1982) Reclamation of scrap rubber vulcanisates III: Reclamation of crushed tyre scrap with dimethylsulfoxide, *Int. Polym.Sci. Technol.*, 55, T/58-62.

Payne, E. (1994), *Rubber World*, May, p.22

Perera, I.B. (2007). Thermo-chemical degradation of natural rubber in a solvent medium, *M.Sc. Thesis*, University of Moratuwa, Sri Lanka.

Phadke A.A., Bhattacharya A.K., Chakraborty S.K., and De S.K. (1983) Studies of vulcanization of reclaimed rubber, *Rubb. Chem. Technol.*, 56, p.726.

Phadke, A.A., Bhowmick, A.K. and De, S.K. (1986). Effect of cryoground rubber on properties of natural rubber. *J. Appl. Polym. Sci.*, 32, 4063.

- Phadke A.A. and De S.K. (1986), *Conserv. Recycl.*, 9, p.271.
- Pritchard G. (1998). Plastics Additives: An A-Z Reference, Chapman & Hall, London.
- Pungor, Erno (1995) *A Practical Guide to Instrumental Analysis*, pp. 181–191. Florida: Boca Raton.
- Rajalakshmi, T. Dhanasekeran, R. and Ramasamy, P (1993), The growth and perfection of urea single crystals from solution, *J. of Mat. Sci. Letters*, 13, p.1797.
- Rajan, V.V., Dierkes, W.K., Joseph, R. and Noordermeer, J.W.M. (2006). Recycling of NR based cured latex material reclaimed with 2,2'-dibenzamido diphenyldisulphide in a truck tyre tread compound. *J. Appl. Polym. Sci.*, 102, pp. 4194-4206.
- Rajan, V.V., Dierkes, W.K., Joseph, R. and Noordermeer, J.W.M. (2006) Science and technology of rubber reclamation with special attention to NR-based waste latex products, *Prog. Polym. Sci.*, 31, pp.811-834.
- Raju, P., Nandanan, V. and Kutty, Sunil K.N. (2007). A study on the use of castor oil as plasticizer in natural rubber compounds. *Progr. Rubber Plast. Technol.*, Vol. 23, Issue No.3, pp.169-180.
-  University of Moratuwa, Sri Lanka. Electronic Theses & Dissertations
 Rattanasom N., Poohsuk, A. and Maknoon, T. (2005). Effect of curing system on the mechanical properties and heat aging resistance of natural rubber / tyre tread reclaimed rubber blends. *Polymer Testing*, September, Vol.24, Issue 6, pp.728-732.
- Roland, Donald G., Faiman, David T. and Jablonowski, Thomas L. (1994) *Tetrabenzylthiuram disulfide / urea cured elastomeric composition*, US Patent 5326828. Retrieved from <http://www.freepatentsonline.com/5326828.html>
- Scheirs, John (1998) Polymer Recycling : Science, Technology and Applications (1st ed., September), Wiley, p.431.
- Schnecko H. (1994), *Kautchuk Gummi Kunststoffe*, 47, p.885.
- Scott, R.L. (1941), *J. Chem. Phys.*, 9, p.440.
- Scuracchio, C.H., Bretas, R.E.S. and Isayev, A.I. (January, 2004). Blends of PS with SBR devulcanized by ultrasound: rheology and morphology, *J. Elastomer Plast.*, 36, pp.45-75.
- Sekhar B.C. (1995), European Patent. 0690091 AL.

Sekhar, B.C., Kormer, V.A. and Sotnikova, E.N. (1996). *Tire Technology International*, p.87.

Sezna, J.A., Dimauro, P.J. and Pawlowski, H.A.(1988). *Rubber Plastics News*, 18, April Issue.

Sezna, J.A., Pawlowski, H.A. and De Coninck, D. (1989). *136th Meeting of the ACS Rubber Division*, Fall, p.9.

Shelton, J.R. (1972). *Rubb. Chem. Technol.*, 45 (2), p.359-369.

Sidewell, J.A. (1997). *The rapra collection of infrared spectra of rubbers, plastics and thermoplastic elastomers* (2nd ed.). Shawbury, Shrewsbury, Shropshire SY 4 4, NR, UK: Rapra Technology// Ltd.

Singleton, R. and Davies, T.L. (1982) Ground vulcanized rubber and reclaimed rubber. In: Blow, C.M., Hepburn, C., Eds. *Rubber Technology & Manufacture*, London, Butterworth, pp.237-242.

Skoog, Douglas A., F. James Holler and Timothy Nieman (1998). *Principles of Instrumental Analysis* (5th ed.) pp. 805–808. New York.

Smit, P.P.A. (1966). *Rheol. Acta*, 5, p.277.

 University of Moratuwa, Sri Lanka
Sombatsompoch, N., Kumnuantip, C. (2003). Rheology, cure characteristics, physical and mechanical properties of tire tread reclaimed rubber / natural rubber compounds. *J. Appl. Polym. Sci.*, 187, pp.123-1731.

Sreeja, T.D. and Kutty, S.K.N. (2000). Cure characteristics and mechanical properties of natural rubber / reclaimed rubber blends. *Polym. Plast. Technol. Eng.*, 39 (3), (2000), pp.501-512.

Sreeja, T.D. and Kutty, S.K.N. (2003). Styrene butadiene rubber / reclaimed rubber blends. *Int. Jour. Polym. Mat.*, 52, pp 599-609.

Stalinski E. (1968) Reclaiming of natural or synthetic rubber, French Pat.1,1517,694.

Stark, F.J., Wagner, D.P., Fesus, E. and Jakush, E. (1999). Paper presented at a meeting of Rubber Division, ACS, 21-24 September, Orlando.

Sun, Ximei and Isayev, A.I. (2007). Modification of crumb rubber. Paper presented at a meeting of the Rubber Division, ACS, 16-18 October, Cleveland, OH, Paper # 105.

Thavamani, P. and Bhowmick, A.K. (1993). *Plast. Rubb. Compos. Process. Appl.*, 20, p.239.

Theodore, A.N., Pett, R.A. and Jackson, D (1998). Cure and mechanical behaviour of elastomeric compounds containing devulcanised materials. *Rubber World*, May, pp.23-25.

Tinker, Andrew J. and Jones, Kevin P. (1980). *Blends of natural rubbers* (Chap. 6), p.620.

Tobolsky, A.V. (1960). *Properties and structure of polymers*. New York: John Wiley & Sons.

Tompa, H. (1949), *Trans. Faraday Soc.*, 45, p.1142.

Tukachinsky A., Schworm D., and Isayev A.I., (1996) Devulcanisation of waste tyre rubber by powerful ultrasound, *Rubb. Chem. Technol.*, 69, p.92.

Twiss D.F., Hughes, A.J. and Amphlett, P.H. (1946) Improvements in or relating to the regeneration of vulcanized synthetic rubber-like materials, British Patent #577,868 and #578,482.

van Duin M., Noordermeer J.W.M., Verbruggen, M.A.L., and van der Does L., (2003) U.S. Pat. 2003013776.

Verbruggen, M.A.L., van der Does, L, Noordermeer, J.W.M., van Duin, M., and Manuel, H.J. (1999) Mechanisms involved in the recycling of NR and EPDM, *Rubb. Chem. Technol.*, 72 (1999) pp.731-740



University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations

Verleye, G.A.L., Roeges, N.P.G. and Del Moor, M.O. (2001). *Easy identification of plastics and rubbers*. Chap. 5, p. 133, Rapra Technology Ltd., UK.

Walters, M.H. and Keyte, D.N. (1962), *Trans. Inst. Rubber Ind.*, T41, p.38.

Walters, M.H. and Keyte, D.N. (1965), Heterogeneous structure in blends of rubber polymers, *Rubb. Chem. Technol.*, 38, p. 62.

Warner W.C. (1994) Methods of devulcanisation, *Rubb. Chem. Technol.*, 67, pp. 559–565.

Watson, E.S. and O'Neill, M.J. (1966) Differential Microcalorimeter, US Patent 3,263,484.

Wunderlich, B. (1990). *Thermal Analysis*. pp. 137–140. New York: Academic Press.

Xu, Z., Losur, N.S. and Gardner, S.D.(1998). *Journal of Advance Materials*, 30, p.11.

Yamashita S. (1981) Reclaimed rubber from rubber scrap (2), *Int. Polym. Sci. Technol.*, 8(12), T / 77-93.

Yamashita S., Kawabata N., Sagan S., Hayashi K., (1977) Reclamation of vulcanized rubbers by chemical degradation. V. Degradation of vulcanized synthetic isoprene rubber by the phenylhydrazine- ferrous chloride system, *J. Appl. Polym. Sci.*, 21, p. 2201.

Yehia, A.A., Ismail, M.N., Hefny, Y.A., Abdel-Bary, E.M. and Mull, M.A. (2004) Mechano-chemical reclamation of waste rubber powder and its effect on the performance of NR and SBR vulcanisates, Vol.36, No.2, pp.109-123.

Yogaratnam, N. (2010) Value addition to natural rubber, Daily News, Thursday, 11th March, Pub. Associated Newspapers of Ceylon Ltd.



University of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

APPENDICES

Appendix I




Figure 1 Variation of initial plasticity of the reclaimed rubber samples with

storage time at constant concentration of the amino compound



University of Moratuwa, Sri Lanka

Electronic Theses & Dissertations

www.lib.mrt.ac.lk




Figure 2 Variation of initial plasticity of the reclaimed rubber samples with

concentration of the amino compound at constant storage time




Figure 3 Variation of initial plasticity of the reclaimed rubber samples with storage time at constant milling time




Figure 4 Variation of initial plasticity of the reclaimed rubber samples with milling time at constant storage time

Appendix II

Calculation of the Cost of Novel Reclaimed Rubber

Table 1 Retail prices of materials and ingredients used for preparation of novel reclaimed rubber

Material / ingredient	Retail price, Rs. (per kg)
GRT	40.00
Amino compound	80.00
Aromatic oil	240.00

Raw material cost:

GRT	- 200g	- Rs. 8.00
Amino cpd	- 15g	- Rs. 1.20
Aromatic oil	- 20g	- Rs. 4.80
<hr/>		
Total	- 235g	- Rs. 14.00
<hr/>		

University of Moratuwa, Sri Lanka.
Material cost of 1kg E Rs. 59.57 ≈ Rs. 60.00 & Dissertations
 www.lib.mrt.ac.lk

Overheads (for 5 minutes):

Electricity	- Rs. 0.90 (430 W mixer)
Labour	- Rs. 6.37 (650/= per day, i.e. for 8.5 working hrs)

Manufacturing cost (per kg):

Material cost	- Rs. 60.00
Electricity	- Rs. 0.90
Labour	- Rs. 6.37

Total (manufacturing cost)	- Rs. 67.27
10% profit	- Rs. 6.73
Selling price	- Rs. 74.00

Note: Prices of two commercially available reclaimed rubbers are Rs. 82.00 and Rs. 140.00.

Appendix III

Publications

J.K. Premachandra, **D.G. Edirisinghe** and M.I.A. De Silva (2011). A novel reclaiming agent for ground rubber tyre (GRT) Part I : Property evaluation of virgin natural rubber (NR) / novel reclaimed GRT blend compounds, *Progr. Rubber Plast. Recycl. Technol.*, Vol.27, No.1.

D.G. Edirisinghe, M.I.A. De Silva and J.K. Premachandra (2011). A novel reclaiming agent for ground rubber tyre (GRT) Part II : Property evaluation of virgin natural rubber (NR) / novel reclaimed GRT revulcanisates, *Progr. Rubber Plast. Recycl. Technol.*, Vol.27, No.3.



University of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk